



PRODUCT REPORT[®]

www.apawood.org

ANTHONY Power Column[®] Anthony Forest Products Company

PR-L264
February 8, 2007

Products: ANTHONY Power Column[®] (APA Custom Product L-264)
Anthony Forest Products Company, 309 N. Washington, El Dorado, AR 71730
(800) 221-2326
<http://www.anthonyforest.com>

1. Basis of the product report:
 - 2006 International Building Code: Section 104.11 Alternative Materials
 - ASTM D 3737 recognized by the 2006 International Building Code and International Residential Code
 - ANSI A190.1 recognized by the 2006 International Building Code and International Residential Code
2. Product description:

Power Column[®] is a Southern Pine structural glued laminated timber manufactured in accordance with ANSI A190.1 using Combination 50 layup combinations recognized in the 2005 National Design Specification (NDS) Supplement, APA Design/Construction Guide: Glulam Design Properties and Layup, Form Y117 (www.apawood.org/publications), and AITC 117. Power Column[®] is used primarily as columns, but can also be used as beams, headers, rafters, or purlins, and is manufactured in nominal widths and depths of 4 through 12 inches, and lengths up to 24 feet.
3. Design properties:

Table 1 lists the design properties for Power Column[®]. The allowable loads for Power Column[®] shall be in accordance with the recommendations provided by the manufacturer (<http://www.anthonyforest.com/powercolumn.pdf>), and with EWS Data File: Design of Structural Glued Laminated Timber Columns, Form Y240 (www.apawood.org/publications), as applicable.
4. Product installation:

Power Column[®] shall be installed in accordance with the recommendations provided by the manufacturer and EWS Technical Note: Glulam Connection Details, Form T300 (www.apawood.org/publications). Permissible filed notching and drilling shall be in accordance with the recommendations provided by the manufacturer.
5. Fire-rated assemblies:

Fire rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer and with APA Product Guide: Fire Rated Systems, Form W305 (www.apawood.org/publications). For one- or two-hour rated glulam columns, Power Column[®] shall be constructed in accordance with ANSI A190.1 and designed in accordance with the recommendations provided by the manufacturer and with EWS Technical Note: Calculating Fire Resistance of Glulam Beams and Columns, Form Y245 (www.apawood.org/publications).
6. Limitations:
 - a) Power Column[®] shall be designed in accordance with the code using the design properties specified in this report.
 - b) Power Column[®] shall have a depth of 2 or more laminations.
 - c) Power Column[®] is produced at Anthony, El Dorado, AR and Washington, GA facilities under a quality control program audited by APA.

d) This report is subject to periodical review and reexamination.

7. Identification:

Power Column® described in this report are identified by a label bearing the manufacturer's name (Anthony Forest Products Company) and/or trademark, the APA assigned plant number (1079 for El Dorado, AR or 1080 for Washington, GA), the product standard (ANSI A190.1), the APA-EWS logo, the report number L264, and a means of identifying the date of manufacture.

Table 1. Design Values for Power Column® Manufactured by Anthony Forest Products Company for Normal Duration of Load ⁽¹⁾

Combination Symbol	Species ⁽²⁾	Grade	Modulus of Elasticity E 10 ⁶ psi	Compression Perpendicular to Grain $F_{c\perp}$ psi	Axially Loaded			Bending about Y-Y Axis				Bending about X-X Axis	
					Tension Parallel to Grain F_t psi	Compression Parallel to Grain		Loaded Parallel to Wide Faces of Laminations				Loaded Perpendicular to Wide Faces of Laminations	
						2 or More Lams	4 or More Lams	2 or 3 Lams	Bending			Shear Parallel to Grain	Bending
								4 or More Lams	3 Lams	2 Lams	See Notes 3 and 4	2 Lams to 15 in. Deep ⁽⁶⁾	See Note 6
1	2	3	4	5	6	7	8	9	10	11	12	13	14
EWS 50	SP	NTD14	1.9	740	1,550	2,300	1,700	2,300	2,100	1,750	260	2,100	300
Wet-use factors			0.833	0.53	0.8	0.73		0.8			0.875	0.8	0.875

Footnotes to Table 1:

- The tabulated design values are for normal duration of loading. For other durations of loading, see applicable building code. The tabulated design values are for dry conditions of use. For wet conditions of use, multiply the tabulated values by the factors shown at the bottom of the table.
- SP = Southern pine.
- The tabulated F_{vy} values are for members of 4 or more lams. The tabulated F_{vy} values shall be multiplied by a factor of 0.95 for 3 lams and 0.84 for 2 lams.
- For members with 5, 7, or 9 lams manufactured from multiple-piece lams with unbonded edge joints, the tabulated F_{vy} values shall be multiplied by a factor of 0.4. For all other members manufactured from multiple-piece lams with unbonded edge joints, the tabulated F_{vy} values shall be multiplied by a factor of 0.5. This adjustment shall be cumulative with the adjustment given in Footnote No. 3.
- The tabulated F_{bx} values are for members without special tension lams up to 15 inches in depth. If the member depth is greater than 15 inches without special tension lams, the tabulated F_{bx} values shall be multiplied by a factor of 0.88. If special tension lams are used, the tabulated F_{bx} values are permitted to be increased by a factor of 1.18 regardless of the member depth.
- For non-prismatic members, notched members, members subject to impact or cyclic loading, or shear design of bending members at connections (NDS 3.4.3.3), the tabulated F_{vx} values shall be multiplied by 0.72.

APA – The Engineered Wood Association is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

**APA – THE ENGINEERED WOOD ASSOCIATION
HEADQUARTERS**

7011 So. 19th St. • Tacoma, Washington 98466

Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: <http://www.apawood.org>

PRODUCT SUPPORT HELP DESK
(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – The Engineered Wood Association, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.